

Especificaciones para lámina de acero al carbón.

LAMINA LISA DE ACERO				
Calibre No.	Espesor (Pulgadas)	Espesor (Mm)	Peso (Lb/ Pie2)	Peso (Kg/M2)
1/2"	0.5	12.7	20.4175	99.695
7/16"	0.4375	11.11	17.8613	87.214
3/8"	0.375	9.53	15.3212	74.811
5/16"	0.3125	7.94	12.765	62.329
1/4"	0.25	6.35	10.2088	49.848
3	0.2391	6.07	9.7586	47.65
4	0.2242	5.69	9.1477	44.667
5	0.2092	5.31	8.5368	41.684
6	0.1943	4.94	7.9419	38.779
3/16"	0.1875	4.76	7.6526	37.366
7	0.1793	4.55	7.3149	35.718
8	0.1644	4.18	6.7201	32.813
9	0.1495	3.8	6.1092	29.83
10	0.1345	3.42	5.4983	26.847
1/8"	0.125	3.18	5.1124	24.963
11	0.1196	3.04	4.8873	23.864
12	0.1046	2.66	4.2764	20.881
13	0.0897	2.28	3.6655	17.898
14	0.0747	1.9	3.0546	14.915
15	0.0673	1.71	2.7491	13.424
1/16"	0.0625	1.59	2.5562	12.482
16	0.0598	1.52	2.4437	11.932
17	0.0538	1.37	2.2025	10.755
18	0.0478	1.21	1.9453	9.499
19	0.0418	1.06	1.7041	8.321
20	0.0359	0.91	1.463	7.144
21	0.0329	0.84	1.3505	6.594
1/32"	0.0312	0.79	1.2701	6.202
22	0.0299	0.76	1.2218	5.966
23	0.0269	0.68	1.0932	5.338
24	0.0239	0.61	0.9807	4.789
25	0.0209	0.53	0.8521	4.161
26	0.0179	0.45	0.7235	3.533
27	0.0164	0.42	0.6752	3.297
1/64"	0.0156	0.4	0.6431	3.14
28	0.0149	0.38	0.6109	2.983
29	0.0135	0.34	0.5466	2.669
30	0.012	0.3	0.4823	2.355
31	0.0105	0.27	0.4341	2.12
32	0.0097	0.25	0.4019	1.963
33	0.009	0.23	0.3698	1.806
34	0.0082	0.21	0.3376	1.649